



Rubber Shelf Life Information- July 2020

	ACM	Material Type	Initial Storage	Extended Storage
Group A	NR	Natural rubber	5 years	2 years
	IR	Polyisopropene		
	BR	Polybutadiene		
	SBR	Styrene-Butadiene		
	AU, EU	Polyurethane		
Group B	ACM	Acrylic	7 years	3 years
	ECO	Epichlorohydrin		
	CR	Neoprene		
	HNBR	Hydrogenated Nitrile		
	IIR	Butyl		
	NBR	Nitrile		
Group C/X	CSM	Chlorosulfonated Polyethylene	10 years	5 years
	EPDM	Ethylene Propylene		
	FKM, FEPM	Fluorocarbon		
	FFKM	Perfluorocarbon		
	VMQ, PMQ, PVMQ	Silicone		
	FVMQ	Fluorosilicone		